



CCTC
三环集团

潮州三环（集团）股份有限公司
Chaozhou Three-Circle (Group) Co., Ltd.
地址：廣東省潮州市鳳塘三環工業城 郵鎮(Post Code)：515646
ADD：San Huan Industrial District, Feng Tang Chao Zhou, Guangdong, China

承 認 書

SPECIFICATION FOR APPROVAL

客户名称：
CUSTOMER：
产品名称：
PARTNAME：
产品规格：
通用系列

SPECIFICATION：

承认书编号
APPROVAL SHEET NO.：
发出日期
ISSUED DATE：

制造 MANUFACTURER			客户 CUSTOMER		
批准 APPROVED	审核 CHECKED	经办 PREPARED	批准 APPROVED	审核 CHECKED	经办 PREPARED
马礼红	王彬彬	张国信			

潮州三环（集团）股份有限公司

地址：中国广东省潮州市凤塘三环工业城

电话：86-768-6855932

传真：86-768-6855921

网址：HTTP：//WWW.CCTC.CC

电话(Tel)：86-768-6855949，685923
E-mail：market@china-threecircle.com

传真(Fax)：(768) 6855928，6855921
Website：<http://www.cctc.cc/>

0



CCTC
三环集团

潮州三环（集团）股份有限公司
Chaozhou Three-Circle (Group) Co., Ltd.
地址：廣東省潮州市鳳塘三環工業城 郵鎮(Post Code)：515646
ADD：San Huan Industrial District, Feng Tang Chao Zhou, Guangdong, China

文件编号	DRAAW108H/0-2017		页数	44
文件名称	多层片式陶瓷电容器(产品承认书)		制订日期	2012.01
版数	制定、修订日期	页数	制定、修订内容	登记者
B/0	2012-01-11	38	新制定	方千军
B/1	2012-08-11	36	增加 2225、1808 尺寸的载带尺寸	王彬彬
C/0	2013-01-10	39	换版	王彬彬
D/0	2014-01-06	39	更新 SGS 报告	王彬彬
E/0	2014-05-06	44	换版	张国信
F/0	2015-02-10	44	换版	张国信
G/0	2016-05-15	44	换版	张国信
H/0	2017-07-01	44	换版	张国信

电话(Tel)：86-768-6855949，685923
E-mail：market@china-threecircle.com

传真(Fax)：(768) 6855928，6855921
Website：<http://www.cctc.cc/>

1



CCTC
三环集团

潮州三环（集团）股份有限公司
Chaozhou Three-Circle (Group) Co., Ltd.
地址：廣東省潮州市鳳塘三環工業城 郵鎮(Post Code)：515646
ADD：San Huan Industrial District, Feng Tang Chao Zhou, Guangdong, China

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

目录

1. 电容器及介质分类	3
2. 产品结构	4
3. 产品规格型号命名规则	5
4. 产品容量范围	6
0402 (1005) 尺寸	6
0603 (1608) 尺寸	8
0805 (2012) 尺寸	10
1206 (3216) 尺寸	12
1210 (3225) 尺寸	14
1808 (4520) 尺寸	16
1812 (4532) 尺寸	17
2220 (5750) 尺寸	19
2225 (5764) 尺寸	21
5. 产品尺寸	22
6. 技术要求和测试条件	23
7. 产品包装	34
8. MLCC 使用注意事项	39



CCTC
三环集团

潮州三环（集团）股份有限公司
Chaozhou Three-Circle (Group) Co., Ltd.
地址：廣東省潮州市鳳塘三環工業城 郵鎮(Post Code)：515646
ADD：San Huan Industrial District, Feng Tang Chao Zhou, Guangdong, China

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

1. 电容器及介质分类 Types of Capacitor and Dielectric Material

※COG：此类介质材料的电容器为Ⅰ类电容器，包括常规、中高压 COG 产品。此类产品电性能稳定，几乎不随温度、电压和时间的变化而变化。适用于低损耗，稳定性要求高的电路中，如滤波器、谐振器和计时电路中。

※COG： The capacitor of this kind dielectric material is considered as ClassⅠcapacitor, including general capacitor and high frequency COG capacitor. The electrical properties of COG capacitor are the most stable one and have little change with temperature, voltage and time. They are suited for applications where low-losses and high-stability are required, such as filters, oscillators, and timing circuits.

※X7R、X5R：此类介质材料的电容器为Ⅱ类电容器，具有较高的介电常数，容量比Ⅰ类电容器高，具有较稳定的温度特性，适用于容量范围广，稳定性要求不高的电路中，如隔直、耦合、旁路、鉴频等电路中。

※ X7R、X5R： material is a kind of material has high dielectric constant. The capacitor made of this kind material is considered as ClassⅡ capacitor whose capacitance is higher than that of classⅠ. These capacitors are classified as having a semi-stable temperature characteristic and used over a wide temperature range, such in these kinds of circuits, DC-blocking, decoupling, bypassing, frequency discriminating etc.

※Y5V：此类介质材料的电容器为Ⅲ类电容器，是所有电容器中介电常数最大的电容器，但其容量稳定性较差，对温度、电压等条件较敏感，适用于要求大容量，温度变化不大的电路中。

※Y5V： The capacitor made of this kind of material is the highest dielectric constant of all ceramic capacitors. They are used over a moderate temperature range in application where high capacitance is required because of its unstable temperature coefficient, but where moderate losses and capacitance changes can be tolerated. Its capacitance and dissipation factors are sensible to measuring conditions, such as temperature and voltage, etc

电话(Tel)：86-768-6855949，685923
E-mail：market@china-threecircle.com

传真(Fax)：(768) 6855928，6855921
Website：<http://www.cctc.cc/>

2


电话(Tel)：86-768-6855949，685923
E-mail：market@china-threecircle.com

传真(Fax)：(768) 6855928，6855921
Website：<http://www.cctc.cc/>

3

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

2. 产品结构 Product Frame



序号	名称
1	陶瓷介质
2	内电极
3	外电极
4	镍层
5	锡层

电话(Tel): 86-768-6855949, 685923
 E-mail: market@china-threecircle.com

传真(Fax): (768) 6855928, 6855921
 Website: <http://www.cctc.co/>

4

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

4. 产品容量范围 Product Capacitance Range

0402 (1005) 尺寸

	COG系列		X7R系列							X5R系列						Y5V系列					
Cp	V _{DC}	50	25	50	25	16	10	6.3	50	25	16	10	6.3	50	25	16	10	6.3			
0R5		A	A																		
1R0		A	A																		
2R0		A	A																		
3R0		A	A																		
4R0		A	A																		
5R0		A	A																		
6R0		A	A																		
7R0		A	A																		
8R0		A	A																		
9R0		A	A																		
100		A	A																		
120		A	A																		
150		A	A																		
180		A	A																		
200		A	A																		
220		A	A																		
270		A	A																		
300		A	A																		
330		A	A																		
390		A	A																		
470		A	A																		
560		A	A																		
680		A	A																		
820		A	A																		
101		A	A	A	A	A	A	A	A	A	A	A	A	A							
121		A	A	A	A	A	A	A	A	A	A	A	A	A							
151		A	A	A	A	A	A	A	A	A	A	A	A	A							
181		A	A	A	A	A	A	A	A	A	A	A	A	A							
201		A	A	A	A	A	A	A	A	A	A	A	A	A							
221		A	A	A	A	A	A	A	A	A	A	A	A	A							
271		A	A	A	A	A	A	A	A	A	A	A	A	A							
331		A	A	A	A	A	A	A	A	A	A	A	A	A							
391		A	A	A	A	A	A	A	A	A	A	A	A	A							
471		A	A	A	A	A	A	A	A	A	A	A	A	A							
561		A	A	A	A	A	A	A	A	A	A	A	A	A							
681		A	A	A	A	A	A	A	A	A	A	A	A	A							
821		A	A	A	A	A	A	A	A	A	A	A	A	A							
102		A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A			

电话(Tel): 86-768-6855949, 685923
 E-mail: market@china-threecircle.com

传真(Fax): (768) 6855928, 6855921
 Website: <http://www.cctc.co/>


6

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

3. 产品规格型号命名规则

General Product Parts Numbering System

(例) (example)



产品的介质特性组别

材质	工作温度范围	温度系数/温度特性
COG	-55℃~+125℃	0±30ppm/℃
X7R	-55℃~+125℃	±15%
X5R	-55℃~+85℃	±15%
Y5V	-30℃~+85℃	+22/-82%

电话(Tel): 86-768-6855949, 685923
 E-mail: market@china-threecircle.com

传真(Fax): (768) 6855928, 6855921
 Website: <http://www.cctc.co/>

5

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

		COG系列			X7R系列						X5R系列						Y5V系列					
Cp	V _{DC}	50	25		50	25	16	10	6.3	50	25	16	10	6.3	50	25	16	10	6.3			
152					Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ			
182					Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ			
222					Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ			
272					Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ			
332					Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ			
472					Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ			
562					Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ			
103					Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ			
153					Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ			
183						Δ	Δ	Δ	Δ		Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ			
223						Δ	Δ	Δ	Δ		Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ			
273						Δ	Δ	Δ	Δ		Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ			
333						Δ	Δ	Δ	Δ		Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ			
393					Δ	Δ	Δ	Δ	Δ		Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ			
473					Δ	Δ	Δ	Δ	Δ		Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ			
563					Δ	Δ	Δ	Δ	Δ		Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ			
683					Δ	Δ	Δ	Δ	Δ		Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ	Δ			
104						Δ	Δ	Δ	Δ		Δ	Δ	Δ	Δ		Δ	Δ	Δ	Δ			
154							Δ	Δ	Δ			Δ	Δ	Δ			Δ	Δ	Δ			
184								Δ	Δ				Δ	Δ			Δ	Δ	Δ			
224									Δ					Δ				Δ	Δ			
274									Δ					Δ				Δ	Δ			
334									Δ					Δ					Δ			
474									Δ									Δ	Δ			
684									Δ					Δ					Δ			
105									Δ					Δ					Δ			

容量公差: COG(0.5pF~4.9pF): B/C; COG(5.0pF~9.9pF): D; COG(≥10pF): F(±1%), G(±2%), J(±5%), K(±10%)

X7R/X5R: J(±5.0%); K(±10%); M(±20%)

Y5V: M(±20%); Z(-20,+80%)

厚度: A: 0.50±0.05mm ;

以上容量仅供参考, 具体容量取决于使用要求。

Tolerance: COG(0.5pF~4.9pF): C COG(5.0pF~9.9pF): D; COG(≥10pF): F(±1%), G(±2%), J(±5%)

X7R/X5R: J(±5.0%); K(±10%); M(±20%)

Y5V: M(±20%); Z(-20,+80%)

Thickness: A: 0.50±0.10mm ;

Above capacitance for reference only, actual cap. Range depends on the standard products.

电话(Tel): 86-768-6855949, 685923
 E-mail: market@china-threecircle.com

传真(Fax): (768) 6855928, 6855921
 Website: <http://www.cctc.co/>

7

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

0603(1608)尺寸

	0603(1608)															
	COG系列				X7R系列				X5R系列				Y5V系列			
Cp V _{DC}	250	100	50	25	250	100	50	25	16	10	6.3	50	25	16	10	6.3
085	c	c	c	c												
180	c	c	c	c												
280	c	c	c	c												
380	c	c	c	c												
480	c	c	c	c												
580	c	c	c	c												
680	c	c	c	c												
780	c	c	c	c												
880	c	c	c	c												
980	c	c	c	c												
100	c	c	c	c												
120	c	c	c	c												
150	c	c	c	c												
180	c	c	c	c												
200	c	c	c	c												
220	c	c	c	c												
270	c	c	c	c												
300	c	c	c	c												
330	c	c	c	c												
390	c	c	c	c												
470	c	c	c	c												
560	c	c	c	c												
680	c	c	c	c												
820	c	c	c	c												
101	c	c	c	c	c	c										
121	c	c	c	c	c	c										
151	c	c	c	c	c	c										
181	c	c	c	c	c	c										
201	c	c	c	c	c	c										
221	c	c	c	c	c	c	c	c	c	c	c	c	c	c	c	c
271	c	c	c	c	c	c	c	c	c	c	c	c	c	c	c	c
331	c	c	c	c	c	c	c	c	c	c	c	c	c	c	c	c
391	c	c	c	c	c	c	c	c	c	c	c	c	c	c	c	c
471	c	c	c	c	c	c	c	c	c	c	c	c	c	c	c	c
561	c	c	c	c	c	c	c	c	c	c	c	c	c	c	c	c
681	c	c	c	c	c	c	c	c	c	c	c	c	c	c	c	c
821	c	c	c	c	c	c	c	c	c	c	c	c	c	c	c	c
102					c	c	c	c	c	c	c	c	c	c	c	c

电话(Tel): 86-768-6855949, 685923
E-mail: m.arket@china-three-circle.com

传真(Fax): (768) 6855928, 6855921
Website: <http://www.cctc.co/>

8

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

	0603(1608)															
	COG系列				X7R系列				X5R系列				Y5V系列			
Cp V _{DC}	250	100	50	25	250	100	50	25	16	10	6.3	50	25	16	10	6.3
152			c	c	c	c	c	c	c	c	c	c	c	c	c	c
182			c	c	c	c	c	c	c	c	c	c	c	c	c	c
222				c	c	c	c	c	c	c	c	c	c	c	c	c
272					c	c	c	c	c	c	c	c	c	c	c	c
332					c	c	c	c	c	c	c	c	c	c	c	c
472					c	c	c	c	c	c	c	c	c	c	c	c
562					c	c	c	c	c	c	c	c	c	c	c	c
682					c	c	c	c	c	c	c	c	c	c	c	c
103					c	c	c	c	c	c	c	c	c	c	c	c
153					c	c	c	c	c	c	c	c	c	c	c	c
183					c	c	c	c	c	c	c	c	c	c	c	c
223					c	c	c	c	c	c	c	c	c	c	c	c
273					c	c	c	c	c	c	c	c	c	c	c	c
333					c	c	c	c	c	c	c	c	c	c	c	c
393					c	c	c	c	c	c	c	c	c	c	c	c
473					c	c	c	c	c	c	c	c	c	c	c	c
563					c	c	c	c	c	c	c	c	c	c	c	c
683					c	c	c	c	c	c	c	c	c	c	c	c
104					c	c	c	c	c	c	c	c	c	c	c	c
154					c	c	c	c	c	c	c	c	c	c	c	c
184					c	c	c	c	c	c	c	c	c	c	c	c
224					c	c	c	c	c	c	c	c	c	c	c	c
274					c	c	c	c	c	c	c	c	c	c	c	c
334					c	c	c	c	c	c	c	c	c	c	c	c
474					c	c	c	c	c	c	c	c	c	c	c	c
684					c	c	c	c	c	c	c	c	c	c	c	c
105					c	c	c	c	c	c	c	c	c	c	c	c
225					c	c	c	c	c	c	c	c	c	c	c	c
475					c	c	c	c	c	c	c	c	c	c	c	c
106										c				c		

容量公差: COG(0.5pF~4.9pF): B/C; COG(5.0pF~9.9pF): D; COG(≥ 10 pF): F($\pm 1\%$), G($\pm 2\%$), J($\pm 5\%$), K($\pm 10\%$)

X7R/X5R: J($\pm 5.0\%$); K($\pm 10\%$); M($\pm 20\%$); Y5V: M($\pm 20\%$); Z(-20,+80%)

厚度: C: $0.80 \pm 0.1\text{mm}$; 以上容量仅供参考, 具体容量取决于使用要求。

Tolerance: COG(0.5pF~4.9pF): C COG(5.0pF~9.9pF): D; COG(≥ 10 pF): F($\pm 1\%$), G($\pm 2\%$), J($\pm 5\%$)

X7R/X5R: J($\pm 5.0\%$); K($\pm 10\%$); M($\pm 20\%$); Y5V: M($\pm 20\%$); Z(-20,+80%)

Thickness: C: $0.80 \pm 0.1\text{mm}$; Above capacitance for reference only, actual cap. Range depends on the standard products.

电话(Tel): 86-768-6855949, 685923
E-mail: m.arket@china-three-circle.com

传真(Fax): (768) 6855928, 6855921
Website: <http://www.cctc.co/>

9

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

0805(2012)尺寸

0805(2012)																								
	COG系列						X7R系列						X5R系列						Y5V系列					
Cp V _{DC}	500	250	100	50	25	16	500	250	100	50	25	16	10	6.3	50	25	16	10	6.3	50	25	16	10	6.3
085	B	B	B	B	B	B																		
180	B	B	B	B	B	B																		
280	B	B	B	B	B	B																		
380	B	B	B	B	B	B																		
480	B	B	B	B	B	B																		
580	B	B	B	B	B	B																		
680	B	B	B	B	B	B																		
780	B	B	B	B	B	B																		
880	B	B	B	B	B	B																		
980	B	B	B	B	B	B																		
100	B	B	B	B	B	B																		
120	B	B	B	B	B	B																		
150	B	B	B	B	B	B																		
180	B	B	B	B	B	B																		
200	B	B	B	B	B	B																		
220	B	B	B	B	B	B																		
270	B	B	B	B	B	B																		
300	B	B	B	B	B	B																		
330	B	B	B	B	B	B																		
390	B	B	B	B	B	B																		
470	B	B	B	B	B	B																		
560	B	B	B	B	B	B																		
680	B	B	B	B	B	B																		
820	B	B	B	B	B	B																		
101	B/D/F	B	B	B	B	B	F	F	F															
121	B/D/F	B	B	B	B	B	F	F	F															
151	B/D/F	B	B	B	B	B	F	F	F															
181	B/D/F	B	B	B	B	B	F	F	F															
201	B/D/F	B	B	B	B	B	F	F	F															
221	B/D/F	B	B	B	B	B	F	F	F	B	B	B	B	B	B	B	B	B	B	B	B	B	B	B
271	B/D/F	B	B	B	B	B	F	F	F	B	B	B	B	B	B	B	B	B	B	B	B	B	B	B
331	B/D/F	B	B	B	B	B	D/F	D/F	D/F	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D
391	B/D/F	B	B	B	B	B	D/F	D/F	D/F	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D
471	B/D/F	B	B	B	B	B	D/F	D/F	D/F	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D
561	D/F	B	B	B	B	B	D/F	D/F	D/F	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D
681		B	B	B	B	B	D/F	D/F	D/F	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D
821		B	B	B	B	B	D/F	D/F	D/F	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D
102		B	B	B	B	B	D/F	D/F	D/F	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D	B/D

产品标准书	编号 Document No.	产品标准书	编号 Document No.
SPECIFICATIONFOR APPROVAL	DRAAW108H/0-2017	SPECIFICATIONFOR APPROVAL	DRAAW108H/0-2017

	1206(3216)
--	------------

[illegible]

传真(Fax): (768) 6855928, 6855921+
Website: <http://www.cctc.cc>

产品标准书	编号 Document No.	产品标准书	编号 Document No.
SPECIFICATIONFOR APPROVAL	DRAAW108H/0-2017	SPECIFICATIONFOR APPROVAL	DRAAW108H/0-2017

容量差, COC($\geq 10\text{pF}$): E(+1%), C(+2%), I(+5%), K(+10%), Y7B/Y5B, I(+5.0%), K(+10%), M(+20%).

容量公差: COG($\geq 10\text{pF}$): F($\pm 1\%$), G($\pm 2\%$), J($\pm 5\%$), K($\pm 10\%$); X7R/X5R: J($\pm 5.0\%$), K($\pm 10\%$); M($\pm 20\%$);
Y5V: M($\pm 20\%$); Z(-20,+80%)
厚度: D: 0.85 $\pm 0.1\text{mm}$, F: 1.25 $\pm 0.2\text{mm}$, H: 1.60 $\pm 0.2\text{mm}$, G: 2.00 $\pm 0.20\text{mm}$ 、M: 2.50 $\pm 0.30\text{mm}$;
以上容量仅供参考, 具体容量取决于使用要求。
Tolerance: COG($\geq 10\text{pF}$): F($\pm 1\%$), G($\pm 2\%$), J($\pm 5\%$); X7R/X5R: J($\pm 5.0\%$); K($\pm 10\%$); M($\pm 20\%$);
Y5V: M($\pm 20\%$); Z(-20,+80%)
Thickness: D: 0.85 $\pm 0.1\text{mm}$; F: 1.25 $\pm 0.2\text{mm}$; H: 1.60 $\pm 0.2\text{mm}$; G: 2.00 $\pm 0.20\text{mm}$ M: 2.50 $\pm 0.30\text{mm}$;
Above capacitance for reference only, actual cap. Range depends on the standard products.

传真(Fax): (768) 6855928, 6855921+
Website: <http://www.cctc.cc>

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

1808(4520)尺寸																
Cp	V _{DC}	1808(4520)										Y5V系列				
		COG系列					X7R系列									
		2000	1000	500	250	50	2000	1000	500	250	100	50	25	16		
101	F	F	F	F	F	F										
121	F	F	F	F	F	F										
151	F	F	F	F	F	F										
181	F	F	F	F	F	F										
201	F	F	F	F	F	F										
221	F	F	F	F	F	F	F	F	F	F	F					
271	F	F	F	F	F	F	F	F	F	F	F					
331	F	F	F	F	F	F	F	F	F	F	F					
391	F	F	F	F	F	F	F	F	F	F	F					
471	F	F	F	F	F	F	F	F	F	F	F					
561	F	F	F	F	F	F	F	F	F	F	F					
681	F	F	F	F	F	F	F	F	F	F	F					
821	F	F	F	F	F	F	F	F	F	F	F					
102	F	F	F	F	F	F	F	F	F	F	F					
222	F	F	F	F	F	F	F	F	F	F	F					
332	F	F	F	F	F	F	F	F	F	F	F					
472			F	F	F	F	F	F	F	F	F					
562				F	F	F	F	F	F	F	F					
103							F	F	F	F	F					
153							F	F	F	F	F					
223								F	F	F	F					
333								F	F	F	F					
473								F	F	F	F					
563									F	F	F					
683										F	F					
104											F	F				
224												F	F			
474													F			
105														F		
225															F	
475																H
106																H

容量容差: COG($\geq 10pF$): F($\pm 1\%$), G($\pm 2\%$), J($\pm 5\%$), K($\pm 10\%$); X7R: J($\pm 5.0\%$); K($\pm 10\%$); M($\pm 20\%$);

Y5V: M($\pm 20\%$); Z(-20,+80%)

厚度: F: $1.25 \pm 0.2mm$, H: $1.60 \pm 0.2mm$; 以上容量仅供参考, 具体容量取决于使用要求。

Tolerance: COG($\geq 10pF$): F($\pm 1\%$), G($\pm 2\%$), J($\pm 5\%$); X7R: J($\pm 5.0\%$); K($\pm 10\%$); M($\pm 20\%$);

Y5V: M($\pm 20\%$); Z(-20,+80%)

Thickness: F: $1.25 \pm 0.2mm$, H: $1.60 \pm 0.2mm$; Above capacitance for reference only, actual cap. Range depends on the standard products.

电话(Tel): 86-768-6855949, 685923
E-mail: market@china-threecircle.com

传真(Fax): (768) 6855928, 6855921
Website: <http://www.cctc.cc/>

16

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

1812 (4532) 尺寸																												
		1812(4532)																										
		COG系列						X7R系列						X5R系列						Y5V系列								
Cp	V _{DC}	3000	2000	1000	500	250	100	50	2000	1000	500	250	100	50	25	16	50	25	16	50	25	16	50	25	16	50	25	16
470	E																											
560	E																											
680	E																											
820	E																											
101	E	F	F	F	F	F		D																				
121	H	F	F	F	F	F		D																				
151	H	F	F	F	F	F		D																				
181	H	F	F	F	F	F		D																				
201	H	F	F	F	F	F		D																				
221	H	F	F	F	F	F		D	F	F	F	F	F	F														
271		F	F	F	F	F		D	F	F	F	F	F	F														
331		F	F	F	F	F		D	F	F	F	F	F	F														
391		F	F	F	F	F		D	F	F	F	F	F	F														
471		F	F	F	F	F		D	F	F	F	F	F	F														
561		F	F	F	F	F		D	F	F	F	F	F	F														
681		F	F	F	F	F		D	F	F	F	F	F	F														
821		F	F	F	F	F		D	F/H	F	F	F	F	F														
102		F	F	F	F	F		D	F/H	F	F	F	F	F														
222									F/H	F	F	F	F	F														
332									F/H	F	F	F	F	F														
472									F/H	F	F	F	F	F														
562										F	F	F	F	F														
682										F/H	F	F	F	F														
103										F/H	F	F	F	F														
153										F/H	F	F	F	F														
223										F/H	F	F	F	F														
333											F	F	F	F														
473										F/H	F	F	F	F														
563											F	F	F	F														
683											F	F	F	F														
104											G	F/H	F	F														
224												F/H	F	F														
334												G	F	F														
474												G	F	F	F	F	F	F	F	F	F							
564												G/H	G/H	G/H	G/H	G/H	G/H	G/H	G/H									
684												G	G	G	G	G	G	G										
105													G	G	G	G	G	G										
225																												
475																												
106																												
226																												
476																												
107																												

电话(Tel): 86-768-6855949, 685923
E-mail: market@china-threecircle.com

传真(Fax): (768) 6855928, 6855921
Website: <http://www.cctc.cc/>

17

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

容量容差: COG($\geq 10pF$): F($\pm 1\%$), G($\pm 2\%$), J($\pm 5\%$), K($\pm 10\%$); X7R/X5R: J($\pm 5.0\%$); K($\pm 10\%$); M($\pm 20\%$);

Y5V: M($\pm 20\%$); Z(-20,+80%)

厚度: D: $0.85 \pm 0.1mm$, E: $1.00 \pm 0.1mm$, F: $1.25 \pm 0.2mm$, H: $1.60 \pm 0.2mm$, G: $2.00 \pm 0.20mm$, M: $2.50 \pm 0.30mm$;

以上容量仅供参考, 具体容量取决于使用要求。

Tolerance: COG($\geq 10pF$): F($\pm 1\%$), G($\pm 2\%$), J($\pm 5\%$); X7R/X5R: J($\pm 5.0\%$); K($\pm 10\%$); M($\pm 20\%$);

Y5V: M($\pm 20\%$); Z(-20,+80%)

Thickness: D: $0.85 \pm 0.1mm$, E: $1.00 \pm 0.1mm$, F: $1.25 \pm 0.2mm$, H: $1.60 \pm 0.2mm$, G: $2.00 \pm 0.20mm$, M: $2.50 \pm 0.30mm$;

Above capacitance for reference only, actual cap. Range depends on the standard products.

电话(Tel): 86-768-6855949, 685923
E-mail: market@china-threecircle.com

传真(Fax): (768) 6855928, 6855921
Website: <http://www.cctc.cc/>

18

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

容量容差: COG($\geq 10\text{pF}$): F($\pm 1\%$), G($\pm 2\%$), J($\pm 5\%$), K($\pm 10\%$); X7R: J($\pm 5.0\%$); K($\pm 10\%$); M($\pm 20\%$);
Y5V: M($\pm 20\%$); Z(-20,+80%)
厚度: E: $1.00 \pm 0.1\text{mm}$, F: $1.25 \pm 0.2\text{mm}$, H: $1.60 \pm 0.20\text{mm}$, G: $2.00 \pm 0.20\text{mm}$, M: $2.50 \pm 0.30\text{mm}$;
以上容量仅供参考, 具体容量取决于使用要求。
Tolerance: COG($\geq 10\text{pF}$): F($\pm 1\%$), G($\pm 2\%$), J($\pm 5\%$); X7R: J($\pm 5.0\%$); K($\pm 10\%$); M($\pm 20\%$);
Y5V: M($\pm 20\%$); Z(-20,+80%)
Thickness: E: $1.00 \pm 0.1\text{mm}$, F: $1.25 \pm 0.2\text{mm}$, H: $1.60 \pm 0.20\text{mm}$, G: $2.00 \pm 0.20\text{mm}$, M: $2.50 \pm 0.30\text{mm}$;
Above capacitance for reference only, actual cap. Range depends on the standard products.

电话(Tel): 86-768-6855949, 685923
E-mail: market@china-threecircle.com

传真(Fax): (768) 6855928, 6855921
Website: <http://www.cctc.cc/>

20

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

5. 产品尺寸 Dimensions

规格: 0402、0603、0805、1206、1210、1808、1812、2220、2225。
Chip Size: 0402,0603,0805,1206,1210,1808,1812,2220 and 2225



规格 Type	L (mm)	W (mm)	e (mm)	g min (mm)	T (mm)				
0402	1.00 ± 0.05	0.50 ± 0.05	$0.15 \sim 0.3$	0.4	0.50 ± 0.05	—	—	—	—
0603	1.60 ± 0.10	0.80 ± 0.10	$0.2 \sim 0.5$	0.5	0.80 ± 0.10	—	—	—	—
0603*	$1.60 \pm 0.15 / -0.10^*$	$0.80 \pm 0.15 / -0.10^*$	$0.2 \sim 0.5$	0.5	$0.80 \pm 0.15 / -0.10^*$	—	—	—	—
0805	2.00 ± 0.10	1.25 ± 0.10	$0.2 \sim 0.7$	0.7	0.60 ± 0.10	0.85 ± 0.10	1.25 ± 0.20	—	—
0805*	$2.00 \pm 0.20^*$	$1.25 \pm 0.20^*$	$0.2 \sim 0.7$	0.7	0.60 ± 0.10	0.85 ± 0.10	1.25 ± 0.20	—	—
1206	3.20 ± 0.20	1.60 ± 0.20	$0.3 \sim 0.8$	1.6	0.85 ± 0.10	1.00 ± 0.10	1.25 ± 0.20	1.60 ± 0.20	—
1206*	$3.20 \pm 0.30^*$	$1.60 \pm 0.30^*$	$0.3 \sim 0.8$	1.6	0.85 ± 0.10	1.00 ± 0.10	1.25 ± 0.20	$1.60 \pm 0.30^*$	—
1210	3.20 ± 0.30	2.5 ± 0.20	$0.3 \sim 0.8$	1.6	0.85 ± 0.10	1.25 ± 0.20	1.60 ± 0.20	2.00 ± 0.20	2.50 ± 0.30
1210*	$3.20 \pm 0.40^*$	$2.5 \pm 0.30^*$	$0.3 \sim 0.8$	1.6	0.85 ± 0.10	1.25 ± 0.20	1.60 ± 0.20	2.00 ± 0.20	2.50 ± 0.30
1808	4.50 ± 0.30	2.0 ± 0.20	$0.3 \sim 1.5$	2.5	1.25 ± 0.20	1.60 ± 0.20	—	—	—
1808*	$4.50 \pm 0.40^*$	$2.0 \pm 0.25^*$	$0.3 \sim 1.5$	2.5	1.25 ± 0.20	1.60 ± 0.20	—	—	—
1812	4.50 ± 0.30	3.2 ± 0.30	$0.3 \sim 1.5$	2.5	0.85 ± 0.10	1.00 ± 0.10	1.25 ± 0.20	1.60 ± 0.20	2.00 ± 0.20
1812*	$4.50 \pm 0.40^*$	$3.2 \pm 0.40^*$	$0.3 \sim 1.5$	2.5	0.85 ± 0.10	1.00 ± 0.10	1.25 ± 0.20	1.60 ± 0.20	2.00 ± 0.20
2220	5.70 ± 0.40	5.0 ± 0.40	$0.3 \sim 1.1$	3.5	1.00 ± 0.10	1.25 ± 0.20	1.60 ± 0.20	2.00 ± 0.20	2.50 ± 0.30
2225	5.70 ± 0.40	6.4 ± 0.40	$0.3 \sim 1.1$	3.5	1.00 ± 0.10	2.00 ± 0.20	2.50 ± 0.30	—	—

*1 标识该规格型号标识为 1uF 及以上规格产品尺寸。

电话(Tel): 86-768-6855949, 685923
E-mail: market@china-threecircle.com

传真(Fax): (768) 6855928, 6855921
Website: <http://www.cctc.cc/>

22

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

2225(5764)尺寸

2225(5764)					
COG系列		X7R系列		Y5V系列	
Cp	V _{DC}	50	400	250	50 25
101	E				
121	E				
151	E				
181	E				
201	E				
221	E				
271	E				
331	E				
391	E				
471	E				
561	E				
681	E				
821	E				
102	E	G	G		
222	E	G	G		
332	E	G	G		
472	E	G	G		
562	E	G	G		
103	E	G	G		
223	E	G	G		
333	E	G	G		
473	E	G	G		
563	E	G	G		
683	G				
104	G	G			
224	G	G			
334	G	G			
474	G	G			
684	G	G			
225				M	M
475				M	M
106					M

容量容差: COG($\geq 10\text{pF}$): F($\pm 1\%$), G($\pm 2\%$), J($\pm 5\%$), K($\pm 10\%$); X7R: J($\pm 5.0\%$); K($\pm 10\%$); M($\pm 20\%$);
Y5V: M($\pm 20\%$); Z(-20,+80%)
厚度: E: $1.10 \pm 0.1\text{mm}$, G: $2.00 \pm 0.20\text{mm}$, M: $2.50 \pm 0.30\text{mm}$; 以上容量仅供参考, 具体容量取决于使用要求。
Tolerance: COG($\geq 10\text{pF}$): F($\pm 1\%$), G($\pm 2\%$), J($\pm 5\%$); X7R: J($\pm 5.0\%$); K($\pm 10\%$); M($\pm 20\%$);
Y5V: M($\pm 20\%$); Z(-20,+80%)
Thickness: E: $1.10 \pm 0.1\text{mm}$, G: $2.00 \pm 0.20\text{mm}$, M: $2.50 \pm 0.30\text{mm}$;
Above capacitance for reference only, actual cap. Range depends on the standard products.

电话(Tel): 86-768-6855949, 685923
E-mail: market@china-threecircle.com

传真(Fax): (768) 6855928, 6855921
Website: <http://www.cctc.cc/>

21

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

6. 技术要求和测试条件 Specification and Test Condition

6.1 外观 Appearance

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
COG/X7R/X5R/Y5V	无损伤或异常 No defects or abnormalities	目视检查 Visual inspection.

6.2 尺寸 Dimensions

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
COG/X7R/X5R/Y5V	在要求的范围内 Within the specified dimensions	用千分尺 Using calipers on micrometer

6.3 容量 Capacitance

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
COG	在要求的容值容差范围内 Within the specified tolerance A: $\pm 0.05\text{pF}$; B: $\pm 0.1\text{pF}$; C: $\pm 0.25\text{pF}$; D: $\pm 0.5\text{pF}$; J: $\pm 5\%$	$1.0 \pm 0.2\text{Vrms}$, $1\text{MHz} \pm 10\%$ ($C_p > 1000\text{pF}$, $1.0 \pm 0.2\text{Vrms}$, $1\text{KHz} \pm 10\%$,)
X7R/X5R	在要求的容值容差范围内 Within the specified tolerance J: $\pm 5\%$; K: $\pm 10\%$; M: $\pm 20\%$	$1.0 \pm 0.2\text{Vrms}$, $1\text{KHz} \pm 10\%$ ($C_p > 10\text{uF}$, $0.5 \pm 0.1\text{Vrms}$, $120 \pm 24\text{Hz}$)
Y5V	在要求的容值容差范围内 Within the specified tolerance M: $\pm 20\%$; Z: -20%, +80%	$1.0 \pm 0.2\text{Vrms}$, $1\text{KHz} \pm 10\%$ ($C_p > 10\text{uF}$, $0.5 \pm 0.1\text{Vrms}$, $120 \pm 24\text{Hz}$)

备注: 测试温度: $25^\circ\text{C} \pm 3^\circ\text{C}$, 测试湿度: $< 70\% \text{RH}$.

电话(Tel): 86-768-6855949, 685923
E-mail: market@china-threecircle.com

23

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

6.4 损耗 Dissipation Factor

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
COG	$C_p < 30\text{pF}$, $Q \geq 400 + 20C_p$; $C_p \geq 30\text{pF}$, $Q \geq 1000$	$1.0 \pm 0.2\text{Vrms}$, $1\text{MHz} \pm 10\%$, 25°C ($C_p > 1000\text{pF}$, $1.0 \pm 0.2\text{Vrms}$, $1\text{KHz} \pm 10\%$)
X7R/X5R	$U_R \geq 100\text{V}$, $DF \leq 3.5\%$ $25\text{V} \leq U_R \leq 50\text{V}$, $DF \leq 3.5\%$ $\leq 5.0\%$, (0402 ≥ 333 , 475 > 0603 ≥ 224 , 475 > 0805 ≥ 684 , 106 > 1206 ≥ 225 , 1210 ≥ 475) $\leq 10\%$ (0603 ≥ 475 , 0805 ≥ 475 , 1206 ≥ 106) $U_R = 16\text{V}$, $DF \leq 5.0\%$ $\leq 7\%$, (105 > 0402 ≥ 104 , 685 > 0603 ≥ 564 , 106 > 0805 ≥ 105 , 1206 ≥ 475 , 1210 ≥ 106): $\leq 10.0\%$, (0402 ≥ 105 , 0603 ≥ 685 , 0805 ≥ 106 , 1206 ≥ 106 , 1210 ≥ 226): $U_R = 10\text{V}$, $DF \leq 7.0\%$ $DF \leq 10\%$ (0402 ≥ 105 , 0603 ≥ 225 , 0805 ≥ 475 , 1206 ≥ 106 , 1210 ≥ 226) $U_R = 6.3\text{V}$, $DF \leq 10\%$	$1.0 \pm 0.2\text{Vrms}$, $1\text{KHz} \pm 10\%$, ($C_p > 10\mu\text{F}$, $0.5 \pm 0.1\text{Vrms}$, 120 $\pm 24\text{Hz}$)
Y5V	$U_R \geq 50\text{V}$, $DF \leq 7.0\%$ $U_R = 25\text{V}$, $DF \leq 7.0\%$ (683 > 0402 ≥ 473 , 474 > 0603 ≥ 104 , 105 > 0805 ≥ 334 , 475 > 1206 ≥ 684 , 106 > 1210 ≥ 105) $DF \leq 9.0\%$ (0402 ≥ 683 , 0603 ≥ 474 , 0805 ≥ 105 , 1206 ≥ 475 , 1210 ≥ 106) $U_R = 16\text{V}$, $DF \leq 9.0\%$ $\leq 12.5\%$ (0402 ≥ 224 , 0603 ≥ 225 , 0805 ≥ 335 , 1206 ≥ 106 , 1210 ≥ 226 , 1812 ≥ 476) $U_R = 10\text{V}$, $DF \leq 12.5\%$ $U_R = 6.3\text{V}$, $DF \leq 15.0\%$	$1.0 \pm 0.2\text{Vrms}$, $1\text{KHz} \pm 10\%$, ($C_p > 10\mu\text{F}$, $0.5 \pm 0.1\text{Vrms}$, 120 $\pm 24\text{Hz}$) 25 $^\circ\text{C}$, 预处理后 48hrs. at 25 $^\circ\text{C}$, 48hrs after annealing
备注：测试温度：25 $^\circ\text{C} \pm 3^\circ\text{C}$ ，测试湿度：<70%RH.		

6.5 绝缘电阻 Insulation Resistance

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
COG/X7R/ X5R/Y5V	$U_R \leq 50\text{V}$, 大于 10 G Ω 或 100 Ω F /CR (大 于其中较小的数值) $U_R \leq 50\text{V}$, More than 10 G Ω or 100 Ω F /CR, whichever is smaller.	$U_R \leq 50\text{V}$ $U_{\text{测}} = U_R$; 充电时间: 60 ± 5 秒 温度: 25 $^\circ\text{C}$ Charge Time: 60 $\pm 5\text{sec}$ Temperature: 25 $^\circ\text{C}$
COG/X7R	$U_R > 50\text{V}$, 大于 4G Ω 或 100 Ω F/CR (大于 其中较小的数值) $U_R > 50\text{V}$, More than 4 G Ω or 100 Ω F/CR, whichever is smaller.	$U_R \leq 400\text{V}$ $U_{\text{测}} = U_R$ $U_R > 400\text{V}$ $U_{\text{测}} = 400\text{V}$; 充电时间: 60 ± 5 秒 温度: 25 $^\circ\text{C}$ Charge Time: 60 $\pm 5\text{sec}$ Temperature: 25 $^\circ\text{C}$

6.6 耐电压 Dielectric Strength

类型 Dielectrics	额定电压范围 Rated voltage range	耐电压性能测试方法 Measuring Method
COG	$U_R \leq 50\text{V}$	施加额定电压的 300% 5 秒, 最大电流不 超过 50mA Force 300% Rated voltage for 5second. Max. current should not exceed 50 mA.
X7R/X5R/Y5V	$U_R \leq 50\text{V}$	施加额定电压的 250% 5 秒, 最大电流不 超过 50mA Force 250% Rated voltage for 5second. Max. current should not exceed 50 mA.
COG/X7R	$100\text{V} \leq U_R < 500\text{V}$	施加额定电压的 200% 5 秒, 最大电流不 超过 50mA Force 200% Rated voltage for 5second. Max. current should not exceed 50 mA.
	$500\text{V} \leq U_R < 1000\text{V}$	施加额定电压的 150% 5 秒, 最大电流不 超过 50mA Force 150% Rated voltage for 5second. Max. current should not exceed 50 mA.
	$1000\text{V} \leq U_R < 2000\text{V}$	施加额定电压的 150% 5 秒, 最大电流不 超过 50mA Force 150% Rated voltage for 5second. Max. current should not exceed 50 mA.
	$U_R \geq 2000\text{V}$	施加额定电压的 120% 5 秒, 最大电流不 超过 30mA Force 120% Rated voltage for 5second. Max. current should not exceed 30 mA.

电话(Tel): 86-768-6855949, 685923
E-mail: market@china-threecircle.com

传真(Fax): (768) 6855928, 6855921
Website: <http://www.cctc.com>

24

电话(Tel): 86-768-6855949, 685923
E-mail: market@china-threecircle.com

传真(Fax): (768) 6855928, 6855921
Website: <http://www.cctc.com>

25


产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

6.7 静电容量温度特性 Temperature Coefficient of Capacitance

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
COG	容量变化在 $\pm 30\text{ppm}/^\circ\text{C}$ 以内 容量漂移在 $\pm 0.2\%$ 或 $\pm 0.05\text{pF}$ 以 内 Temperature coefficient within $\pm 30\text{ppm}/^\circ\text{C}$; C_p drift within $\pm 0.2\%$ or $\pm 0.05\text{pF}$	按系列温度顺序测试电容量 Measure capacitance under follow table list temperature: 步骤 STEP COG, X7R X5R Y5V 1 25 ± 2 25 ± 2 25 ± 2 2 -55 ± 3 -55 ± 3 -30 ± 3 3 25 ± 2 25 ± 2 25 ± 2 4 125 ± 3 85 ± 3 85 ± 3 5 25 ± 2 25 ± 2 25 ± 2
	容量变化在 $\pm 15\%$ 以内 Capacitance change within $\pm 15\%$	
X7R/X5R	容量变化在 $\pm 15\%$ 以内 Capacitance change within $\pm 15\%$	
Y5V	容量变化在 $+22\%$, -82% 以内 Capacitance change within $+22\%$, -82%	1) COG 容量漂移的计算方法为：用步骤 3 测量的电容量 值除以在第 1、3 和 5 步骤测量得到的误差的最大 值和最小值的差。 温度系数的计算以第 3 步骤测量电容量为参考。 The capacitance drift is calculated by dividing the differences between the maximum and minimum measured values in the step 1,3 and 5. The temperature coefficient is determined using the Capacitance measured in step 3 as a reference. 2) X7R、X5R 和 Y5V X7R、X5R 和 Y5V 与 25 $^\circ\text{C}$ 时的电容量相比较，电容量在温度范 围内的变化在要求的范围之内。 The ranges of capacitance change compared within the above 25 $^\circ\text{C}$ value over the temperature ranges shall be within the specified ranges.

6.8 附着力 Adhesion

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
COG/X7R/X5R/ Y5V	端电极无松动，也无其它不良现 象 No removal of the terminations or other defect shall occur.	施加 6N 的压力，并保持 10 ± 1 秒 The pressurizing force shall be 6N (=600gf) and the duration of application shall be 10 $\pm 1\text{sec}$. 

6.9 可焊性 Solderability of Termination

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
COG X7R/X5R Y5V	端电极挂锡面积不小于 95%，针孔或 粗糙面积小于 5% 95% min. coverage of both terminal electrodes and less than 5% have pin holes or rough spots.	锡炉温度：245 $\pm 5^\circ\text{C}$ 浸入时间：2 ± 1 秒 两侧端电极完全浸入焊锡炉 Solder temperature: 245 $\pm 5^\circ\text{C}$ Dipping time: 2 ± 1 seconds. Completely soak both terminal electrodes in solder

6.10 耐焊性 Resistance to leaching

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
COG X7R/X5R Y5V	端电极挂锡面积不小于 95%，针孔或 粗糙面积小于 5%，外观无开裂 95% min. coverage of both terminal electrodes and less than 5% have pin holes or rough spots. No remarkable visual damage.	预热：120 $^\circ\text{C}$ ~150 $^\circ\text{C}$ /60 秒 锡炉温度：270 $\pm 5^\circ\text{C}$ 浸入时间：10 ± 1 秒 两侧端电极完全浸入焊锡炉 Solder temperature: 270 $\pm 5^\circ\text{C}$ preheated: 120 $^\circ\text{C}$ ~150 $^\circ\text{C}$ /60sec Dipping time: 10 ± 1 seconds. Completely soak both terminal electrodes in solder

电话(Tel): 86-768-6855949, 685923
E-mail: market@china-threecircle.com

传真(Fax): (768) 6855928, 6855921
Website: <http://www.cctc.com>

26


电话(Tel): 86-768-6855949, 685923
E-mail: market@china-threecircle.com

传真(Fax): (768) 6855928, 6855921
Website: <http://www.cctc.com>

27

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

6.11 端电极结合强度 Bending

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
COG	无可见损伤： 容量变化小于等于±5% 或 0.5 PF No remarkable visual damage Cp change ≤ ±5% or ≤ 0.5 pF	将片状电容器安装在测试夹具上，按图所示方向以 1.0mm/s 的速率施加压力，弯曲 1mm。 Solder the capacitor on testing substrate and put it on testing stand. The middle part of substrate shall successively be pressurized by pressuring rod at a rate of about 1.0mm/sec. Until the deflection become means of the 1.0mm.
X7R/X5R	无可见损伤： 容量变化小于等于±10% No remarkable visual damage Cp change ≤ ±10%	
Y5V	无可见损伤： 容量变化小于等于 ±30% No remarkable visual damage Cp change ≤ ±30%	

电话(Tel): 86-768-6855949, 685923
 E-mail: market@china-three-circle.com

传真(Fax): (768) 6855928, 6855921
 Website: <http://www.cctc.cc/>

28

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

6.13 温度快速循环 Temperature Cycle

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
COG	无明显可见损伤 容量变化在±2.5%或 ±0.25pF (取较大值) 以内 No remarkable visual damage Cp change within ±2.5% or ±0.25pF, whichever is larger.	按下列步骤进行 5 次循环： To perform 5 cycles of the stated environment 步骤 Step 1 温度 时间 下限类别温度 30min +0/-3℃ Min. operating Temp.+0/-3℃ 2 25℃ 2~3 min 3 上限类别温度 30 min +3/-0℃ Max. operating Temp.+3/-0℃ 4 25℃ 2~3 min
X7R/X5R	无明显可见损伤 容量变化在±7.5%以内 No remarkable visual damage Cp change within ±7.5%	在室温下放置 24±2 (COG) 或 48±4(X7R、X5R、Y5V) 小时以后测量 *高介电常数电容器的初始值测量在 140~150℃ 进行 1 小时的热处理后在室温下放置 48±4 小时测量初始值
Y5V	无明显可见损伤 容量变化在±20%以内 No remarkable visual damage Cp change within ±20%	Measurement to be made after being kept at room temperature for 24±2hrs (COG) or 48±4hrs (X7R, X5R, Y5V) at room temperature, then measure. *Initial measurement for high dielectric constant type Perform a heat treatment at 140~150℃ for 1hr and let sit for 48±4hrs at room temperature. Perform the initial measurement.

电话(Tel): 86-768-6855949, 685923
 E-mail: market@china-three-circle.com

传真(Fax): (768) 6855928, 6855921
 Website: <http://www.cctc.cc/>

30

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

6.12 耐焊接热 Resistance to Soldering Heat

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
COG	无明显可见损伤 容量变化在±2.5%或 ±0.25pF (取较大值) 以内 DF 满足产品初始值的要求 IR 满足产品初始值的要求 No remarkable visual damage Cp change within ±2.5% or ±0.25pF, whichever is larger. DF meets initial standard value. IR meets initial standard value.	焊接温度: 270±5℃ 预热: 120~150℃ 60 秒 浸入时间: 10±1 秒 在室温下放置 24±2 (COG) 或 48±4(X7R、X5R、Y5V) 小时以后测量 试验后在标准条件下恢复 *高介电常数电容器的初始值测量在 140~150℃ 进行 1 小时的热处理后在室温下放置 48±4 小时测量初始值 Soldering temperature: 270±5℃ Preheating: 120~150℃ 60sec. Dipping time: 10±1 seconds. Measurement to be made after being kept at room temperature for 24±2 (COG) or 48±4(X7R, X5R, Y5V) hours. Recov ery for the following period under the standard condition after test.
X7R/X5R	无明显可见损伤 容量变化在±7.5%以内 DF 满足产品初始值的要求 IR 满足产品初始值的要求 No remarkable visual damage Cp change within ±7.5% DF meets initial standard value. IR meets initial standard value.	*Initial measurement for high dielectric constant type Perform a heat treatment at 140~150℃ for 1hr and let sit for 48±4hrs at room temperature. Perform the initial measurement.
Y5V	无明显可见损伤 容量变化在±20%以内 DF 满足产品初始值的要求 IR 满足产品初始值的要求 No remarkable visual damage Cp change within ±20% DF meets initial standard value. IR meets initial standard value.	

电话(Tel): 86-768-6855949, 685923
 E-mail: market@china-three-circle.com

传真(Fax): (768) 6855928, 6855921
 Website: <http://www.cctc.cc/>

29

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

6.14 稳态湿热 Moisture Resistance ,steady state

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
COG	外观无明显可见损伤 容量变化在±5%或 ±0.5pF (取较大值) 以内 Cp<10pF, Q≥200+10Cp; 10≤Cp<30pF, Q≥275+2.5Cp Cp≥30pF, Q≥350 IR: 大于 1000MΩ 或 50Ω-F(取较小值) No remarkable visual damage Cp change within ±5% or ±0.5pF, whichever is larger. Cp<10pF, Q≥200+10Cp; 10≤Cp<30pF, Q≥275+2.5Cp Cp≥30pF, Q≥350 R*C≥1000MΩ or 50Ω-F, whichever is smaller	测试温度: 40±2℃ 湿度: 90~95% RH 测试时间: 500 ±12hrs 在室温下放置 24±2 (COG) 或 48±4(X7R、X5R、Y5V) 小时以后测量 *高介电常数电容器的初始值测量在 140~150℃ 进行 1 小时的热处理后在室温下放置 48±4 小时测量初始值 Test temperature: 40±2℃ Humidity: 90~95% RH Testing time: 500 ±12hrs
X7R/X5R	外观无明显可见损伤 容量变化在±12.5%以内 DF 为初始值的 2 倍以下 IR: 大于 1000MΩ 或 50Ω-F(取较小值) Cp change within ±12.5% DF: Not more than 2 times of initial value R*C≥1000MΩ or 50Ω-F, whichever is smaller	Measurement to be made after being kept at room temperature for 24±2hrs (COG) or 48±4hrs (X7R, X5R, Y5V) *Initial measurement for high dielectric constant type Perform a heat treatment at 140~150℃ for 1hr and let sit for 48±4hrs at room temperature. Perform the initial measurement.
Y5V	外观无明显可见损伤 容量变化在±30%以内 DF 为初始值的 1.5 倍以下 IR: 大于 1000MΩ 或 50Ω-F(取较小值) No remarkable visual damage Cp change within ±30% DF: Not more than 1.5 times of initial value R*C≥1000MΩ or 50Ω-F, whichever is smaller	

电话(Tel): 86-768-6855949, 685923
 E-mail: market@china-three-circle.com

传真(Fax): (768) 6855928, 6855921
 Website: <http://www.cctc.cc/>

31

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

6.15 耐湿负荷 Damp heat with load

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
COG	外观无明显可见损伤 容量变化在±7.5%或±0.75pF (取较大值) 以内 Cp<30pF, Q≥100+10/3°Cp Cp≥30pF, Q≥200 IR: 大于 500MΩ 或 25Ω·F(取较小值) No remarkable visual damage Cp change≤7.5% or ±0.75pF, whichever is larger. Cp<30pF, Q≥100+10/3°Cp Cp≥30pF, Q≥200 R°C≥500MΩ or 25Ω·F, whichever is smaller	测试温度: 40±2°C 湿度: 90~95% RH 电压: 额定电压 测试时间: 500 ±12hrs 在室温下放置 24±2 (COG) 或 48±4(X7R、X5R、Y5V) 小时以后测量 *在 40±2°C 温度下, 将电容器加额定直流电压 1hrs. 去掉电压, 将电容器在室温下放置 48±4hrs 测量初始电容值。 Test temperature: 40±2°C Humidity: 90~95% RH Voltage: 100% of the rated voltage Testing time: 500 ±12hrs
X7R/X5R	外观无明显可见损伤 容量变化在±12.5%以内 DF 为初始值的 2 倍以下 IR: 大于 500MΩ 或 25Ω·F(取较小值) No remarkable visual damage Cp change≤12.5% DF: Not more than 2 times of initial value R°C≥500MΩ or 25Ω·F, whichever is smaller	Measurement to be made after being kept at room temperature for 24±2hrs (COG) or 48±4hrs (X7R, X5R, Y5V) *Apply the rated DC voltage for 1 hour at 40±2°C. Remove and let sit for 48±4hrs at room temperature. Perform the initial measurement.
Y5V	外观无明显可见损伤 容量变化在±30%以内 DF 为初始值的 1.5 倍以下 IR: 大于 500MΩ 或 25Ω·F(取较小值) No remarkable visual damage Cp change≤30% DF: Not more than 1.5 times of initial value R°C≥500MΩ or 25Ω·F, whichever is smaller	Measurement to be made after being kept at room temperature for 24±2hrs (COG) or 48±4hrs (X7R, X5R, Y5V) *Apply the rated DC voltage for 1 hour at 40±2°C. Remove and let sit for 48±4hrs at room temperature. Perform the initial measurement.

备注: 该项可靠性试验仅适用于常规产品, 不适用于中高压产品。

电话(Tel): 86-768-6855949, 685923
E-mail: market@china-three-circle.com

传真(Fax): (768) 6855928, 6855921
Website: <http://www.cctc.cc/>

32

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

6.16 耐久性 Life Test

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
COG	外观无明显可见损伤 容量变化在±3%或±0.3pF (取较大值) 以内 容量在 30pF 以上, Q≥350 容量在 10 pF 以上且小于 30 pF, Q≥275+(2.5* Cp) 容量小于 10pF, Q≥200+10* Cp IR: 大于 1000MΩ 或 50Ω·F(取较小值) No remarkable visual damage Cp change≤3% or ±0.3pF, whichever is larger. Q≥350 (Cp≥30 pF) Q≥275+(2.5* Cp) (10 pF≤Cp<30 pF) Q≥200+10* Cp (Cp<10 pF) R°C≥1000MΩ or 50Ω·F, whichever is smaller	测试温度: 上限类别温度±3°C 电压: U _g <100V 1.5 倍额定电压 测试时间: 1000 小时 在室温下放置 24±2 (COG) 或 48±4(X7R、X5R、Y5V) 小时以后测量 *高介电常数电容器的初始值测量 在上限类别温度±3°C, 将电容器加 1.5 倍额定直流电压 1 小时 去掉电压, 将电容器在室温下放置 48±4hrs 测量初始电容值 Test temperature: Max. Operating Temp. ±3°C Voltage: U _g <100V 150% of the rated voltage Testing time: 1000 hrs
X7R/X5R	外观无明显可见损伤 容量变化在±12.5%以内 DF 为初始值的 2 倍以下 IR: 大于 1000MΩ 或 50Ω·F(取较小值) No remarkable visual damage Cp change≤12.5% DF: Not more than 2 times of initial value R°C≥1000MΩ or 50Ω·F, whichever is smaller	Measurement to be made after being kept at room temperature for 24±2hrs (COG) or 48±4hrs (X7R, X5R, Y5V) *Initial measurement for high dielectric constant type Apply 150% of the rated DC voltage for one hour at the maximum operating temperature ±3°C. Remove and let sit for 48±4hrs at room temperature. Perform the initial measurement
Y5V	外观无明显可见损伤 容量变化在±30%以内 DF 为初始值的 1.5 倍以下 IR: 大于 1000MΩ 或 50Ω·F(取较小值) No remarkable visual damage Cp change≤30% DF: Not more than 1.5 times of initial value R°C≥1000MΩ or 50Ω·F, whichever is smaller	Measurement to be made after being kept at room temperature for 24±2hrs (COG) or 48±4hrs (X7R, X5R, Y5V) *Initial measurement for high dielectric constant type Apply 150% of the rated DC voltage for one hour at the maximum operating temperature ±3°C. Remove and let sit for 48±4hrs at room temperature. Perform the initial measurement

备注: 该项可靠性试验仅适用于常规产品, 不适用于中高压产品。

电话(Tel): 86-768-6855949, 685923
E-mail: market@china-three-circle.com

传真(Fax): (768) 6855928, 6855921
Website: <http://www.cctc.cc/>

33

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

7. 产品包装 Packing


7.1 袋式散裝 Bulk Packing

10000 个/袋或按客户要求。Standard packing 10Kpcs/bag; others are according to customer request.

7.2 编带式包装 Tape Packing

规格	尺寸 Size (mm)			编带数量(个/盘 pcs/reel)	
Type	长度 L	宽度 W	厚度 T	纸带 Paper Tape	塑料带 Plastic Tape
0402	1.0	0.5	0.5	10,000	N/A
0603	1.6	0.8	0.8	4,000	N/A
0805	2.0	1.25	<0.85	4,000	N/A
			≥0.85	N/A	2,000 (或 3000)
1206	3.2	1.6	≤0.85	4,000	N/A
			>0.85	N/A	2,000 (或 3000)
1210	3.2	2.5	≤1.25	N/A	2,000
			>1.25	N/A	2,000
1808	4.5	2.0	≤1.25	N/A	1,000
1812	4.6	3.2	≤1.25	N/A	1,000
			>1.25	N/A	1,000
2220	5.7	5.0	≤1.25	N/A	700
			>1.25	N/A	700
2225	5.7	6.4	>1.25	N/A	700

7.2.1 纸带尺寸 Dimensions of Packing Paper



Type	A	B	C	D	T
0402	0.65±0.10	1.15±0.10	2.0±0.05	2.0±0.05	0.8max
0603	1.05±0.10	1.85±0.10	4.0±0.10	2.0±0.10	1.1max
0805	1.55±0.15	2.3±0.15	4.0±0.10	2.0±0.10	1.1max
1206	1.95±0.15	3.5±0.15	4.0±0.10	2.0±0.10	1.1max

(单位 unit: 毫米 mm)


电话(Tel): 86-768-6855949, 685923
E-mail: market@china-three-circle.com

传真(Fax): (768) 6855928, 6855921
Website: <http://www.cctc.cc/>


34

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017


7.2.2 塑料带尺寸 Dimensions of Embossed Packing



7.2.3 编带盘尺寸 Dimensions of Reel



7.2.4 编带方式 Taping Figure



电话(Tel): 86-768-6855949, 685923
E-mail: market@china-three-circle.com

传真(Fax): (768) 6855928, 6855921
Website: <http://www.cctc.cc/>


35



CCTC
三环集团


潮州三环（集团）股份有限公司
Chaozhou Three-Circle (Group) Co., Ltd.
地址：广东省潮州市凤塘三墩工瓷城 邮编(Post Code)：515646
ADD：San Huan Industrial District, Feng Tang Chao Zhou, Guangdong, China

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017



7.2.5 编带方法 Taping Method

- 包装电容器的编带是顺时针卷绕的，由上往下的方向拉出编带时，传送孔处于编带的右侧。
- 在编带的前端，至少留出 5 个间距的引出带。
- 在编带时，必须按下图留出引出带部分或空白部分。
- 在盘带的安装中的产品装错的数量每盘必须小于表示数量的 0.1% 或 1 个为限，不连续发生错误。
- 上胶带和下胶带不应超出编带的边缘，不能挡住传送孔。
- 传送孔的累计误差为 10 个间距：±0.3 毫米以内。
- 上胶带的剥离力矩应在 0.1 至 0.6 牛顿以内，其方向如下图所示。
- Tapes for capacitors are wound clockwise. The sprocket holes are to the right as the tape is pulled toward the user.
- The top tape and base tape are not attached at the end of the tape for a minimum of 5 pitches.
- Part of the leader and part of the empty tape shall be attached to the end of the tape as follows.
- Missing capacitors number within 0.1% of the number per reel or 1pc, whichever is greater, and are not continuous.
- The top tape and bottom tape shall not protrude beyond the edges of the tape and shall not cover sprocket holes.
- Cumulative tolerance of sprocket holes, 10 pitches: ±0.3mm.
- Peeling off force: 0.1 to 0.6N in the direction shown down.



电话(Tel): 86-768-6855949, 685923
E-mail: market@china-threecircle.com

传真(Fax): (768) 6855928, 6855921
Website: <http://www.cctc.cc/>

36



CCTC
三环集团

潮州三环（集团）股份有限公司
Chaozhou Three-Circle (Group) Co., Ltd.
地址：广东省潮州市凤塘三墩工瓷城 邮编(Post Code)：515646
ADD：San Huan Industrial District, Feng Tang Chao Zhou, Guangdong, China

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

7.2.7.2 内包装盒 Inner Box

7.2.7.2.1 包装盒尺寸 Size

L	W	H
18.5cm	6.5cm	19cm

7.2.7.2.2 数量: 40Kpcs /盒

1 盘=4000PCS 1 REEL=4,000PCS

1 包装盒=4,000PCS × 10 盘 =40,000PCS 1 INNER BOX=4,000PCS × 10 REEL=40,000PCS




CCTC
三环集团

潮州三环（集团）股份有限公司
Chaozhou Three-Circle (Group) Co., Ltd.
地址：广东省潮州市凤塘三墩工瓷城 邮编(Post Code)：515646
ADD：San Huan Industrial District, Feng Tang Chao Zhou, Guangdong, China

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

7.2.6 产品标签 Reel Label



标签内容 The Contents of Label

- (1) TCC 0805 Y5V 474 Z 250 D I
- (2) ① ② ③ ④ ⑤ ⑥ ⑦ ⑧
- (3) ①陶瓷电容器代号 Code of Ceramic Capacitor
- (4) ②尺寸 chip size, ③温度特性 dielectrics, ④容量 capacitance, ⑤容量公差 tolerance, ⑥额定电压 rated voltage, ⑦厚度 thickness, ⑧包装 packing
- (5) ②产品批号 Lot. No.: C120889A
- (6) ③数量 Qty: 4000pcs
- (7) ④RoHS: GREEN PARTS 绿色物料

7.2.7.外包装 Package

7.2.7.1 包装箱 Carton

7.2.7.1.1 包装箱尺寸 Carton Size

L	W	H
41.0cm	38.5cm	20.2cm

7.2.7.1.2 数量: 240Kpcs /箱 The Quantity: 240Kpcs /one carton

1 内包装盒=40,000PCS 1 INNER BOX=40,000PCS

1 包装箱 =40,000PCS × 6 包装盒=240,000PCS 1 CARTON=40,000PCS × 6 BOX=240,000PCS

RoHS 标识(根据客户要求张贴) according to customer request

电话(Tel): 86-768-6855949, 685923
E-mail: market@china-threecircle.com

传真(Fax): (768) 6855928, 6855921
Website: <http://www.cctc.cc/>

37



CCTC
三环集团

潮州三环（集团）股份有限公司
Chaozhou Three-Circle (Group) Co., Ltd.
地址：广东省潮州市凤塘三墩工瓷城 邮编(Post Code)：515646
ADD：San Huan Industrial District, Feng Tang Chao Zhou, Guangdong, China

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

8. MLCC 使用注意事项 Precautions on the use of MLCC

8.1 电路板设计 PCB Design

8.1.1 电路板图案设计 Design of Land-patterns

下面图和表格给出了部分推荐的设计图案，可以防止安装时焊锡量过多。同时也给出了不正确的图案。

The following diagrams and tables show some examples recommended patterns to prevent excessive solder amounts (larger fillets which above the component end terminations)

Examples of improper pattern designs are also shown.



电路板设计推荐图案尺寸:

Recommended land dimensions for a typical chip capacitor land patterns for PCBs

波峰焊接时推荐设计的尺寸 (单位: mm):

Recommended land dimensions for wave-soldering (unit: mm)

规格 SIZE		0603	0805	1206
尺寸	L	1.6	2.0	3.2
	W	0.8	1.25	1.6
A		0.8~1.0	1.0~1.4	1.8~2.5
B		0.5~0.8	0.8~1.5	0.8~1.7
C		0.6~0.8	0.9~1.2	1.2~1.6



再流焊接时推荐设计的尺寸 (单位: mm)

Recommended land dimensions for reflow-soldering (unit: mm)

规格 SIZE		0402	0603	0805	1206	1210	1808	1812	2220	2225
尺寸	L	1.0	1.6	2.00	3.2	3.2	4.5	4.5	5.7	5.7
	W	0.5	0.8	1.25	1.6	2.5	2.0	3.2	5.0	6.4
A		0.35~0.45	0.6~0.8	0.8~1.2	1.8~2.5	1.8~2.5	2.5~3.4	2.5~3.4	4.0~4.6	4.0~4.6
B		0.40~0.50	0.6~0.8	0.8~1.2	1.0~1.5	1.0~1.5	1.8~2.0	1.8~2.0	2.0~2.2	2.0~2.2
C		0.45~0.55	0.6~0.8	0.9~1.6	1.2~2.0	1.6~3.2	1.4~1.8	2.3~3.5	3.5~4.8	5.0~6.2

过量的焊锡会影响产品抵抗机械应力的能力，因此设计图案时应引起注意。

Excess solder can affect the ability of chips to withstand mechanical stresses. Therefore, please take proper precautions when designing land-patterns.

在应用中一些焊接好与坏的情况:

Examples of good and bad solder application

电话(Tel): 86-768-6855949, 685923
E-mail: market@china-threecircle.com

传真(Fax): (768) 6855928, 6855921
Website: <http://www.cctc.cc/>

38

电话(Tel): 86-768-6855949, 685923
E-mail: market@china-threecircle.com

传真(Fax): (768) 6855928, 6855921
Website: <http://www.cctc.cc/>

39

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

项目 Item	不推荐结构 Not recommended	推荐结构 Recommended
片状元件和带引线的元件的混合焊接 Mixed mounting of SMD and leaded component		
靠近底座的焊接 Component placement close to the chassis		
在片状元件附近带引线元件的焊接 Hand-soldering of leaded components near mounted components		

8.1.2 图案结构 Pattern configurations

下面是电容器安装好与坏的例子。选择贴装位置，应尽可能减小电路板在弯曲时受到的机械应力。

The following are examples of good and bad capacitor layout, SMD capacitors should be located to minimize any possible mechanical stresses from board warp or deflection..

	不推荐结构 Not recommended	推荐结构 Recommended
电路板弯曲 Deflection of the board		


对于电路板分拨的电容器，在分拨时受到的机械应力大小与电容器的安装有关。下面推荐了一些好的设计。To layout the capacitors for the breakaway PC board, it should be noted that the amount of mechanical stresses given depending on capacitor layout. The example below shows recommendations for better design.

电话(Tel): 86-768-6855949, 685923
 E-mail: market@china-threecircle.com

传真(Fax): (768) 6855928, 6855921
 Website: <http://www.cctc.cc/>

40

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017



在沿着分拨线分拨电路板时，对产品施加的机械应力与使用的方法关系很大。分析电路板时片状元件受到的疲劳按照如下顺序增大：分折、剪切、V 型槽、穿孔。因此，贴装时应该考虑电路板的分拨过程。

When breaking PC boards along their perforations, the amount of mechanical stress on the capacitors can vary according to the method used. The following methods are listed in order from least stressful to most stressful: push-back, slit, -grooving, and perforation. Thus, any ideal SMD capacitor layout must also consider the PCB splitting procedure.

8.2 自动贴装注意事项 Considerations for automatic placement

贴装机的调整 Adjustment of mounting machine

- ①. 产品在电路板贴装时，不应该受到过大的冲击。
- ②. 必须定期对吸头和定位爪进行检查、维修和更换
- ①. Excessive impact load should not be imposed on the capacitors when mounting the PC boards.
- ②. The maintenance and inspection of the mounters should be conducted periodically.

	不推荐结构 Not recommended	推荐结构 Recommended
单面贴装 Single-sided mounting		
双面贴装 Double-sided mounting		

电话(Tel): 86-768-6855949, 685923
 E-mail: market@china-threecircle.com

传真(Fax): (768) 6855928, 6855921
 Website: <http://www.cctc.cc/>

41

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017


8.3 推荐焊接曲线 Recommended soldering profile

8.3.1 说明: ① 产品推荐使用回流焊接工艺; ② 大尺寸产品适用于回流焊接工艺

Re: ①flow Soldering is recommended; ②flow soldering is suitable for bigger size MLCCs


8.3.2 锡铅焊接曲线 Recommended Sn&Pb soldering profile

回流焊 Reflow soldering



注意 Caution


- ①. 理想状况的焊锡高度为电容器厚度的 1/3 ~1/2, 如下图所示:
- ①.The ideal condition is to have solder mass (fillet) controlled to 1/2 to 1/3 of the thickness of the capacitor, as shown below:



- ②. 过长的焊接时间会影响端头的可焊性, 焊接时间尽可能保持与推荐时间一致。

- ②. Because excessive dwell times can detrimentally affect solderability, soldering duration should be kept as close to recommended times as possible.

波峰焊 Wave solder profile



电话(Tel): 86-768-6855949, 685923
 E-mail: market@china-threecircle.com

传真(Fax): (768) 6855928, 6855921
 Website: <http://www.cctc.cc/>

42

产品标准书	编号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108H/0-2017

注意 Caution

- ①. 确保电容器充分预热。
- ②. 产品预热和焊接温度差不超过 100~130°C。
- ③. 焊接后尽可能慢速冷却。
- ①. Make sure the capacitors are preheated sufficiently.
- ②. The temperature difference between the capacitor and melted solder should not be greater than 100 to 130°C.
- ③. Cooling after soldering should be gradual as possible.

手工焊接 Hand soldering

条件:


预热	烙铁头温度	烙铁功率	烙铁头直径	焊接时间	锡膏量	限制条件
$\Delta \leq 130^{\circ}\text{C}$	最高350°C	最大20W	建议1mm	最长5s	$\leq 1/2$ 芯片厚度	请勿使用烙铁头直接接触陶瓷原件

注意 Caution

- ①. 用尖端最大直径 1.0mm 功率 20W 的焊接烙铁。
- ②. 焊接烙铁不要直接接触产品。
- ①. Use a 20w soldering iron with a maximum tip diameter of 1.0mm.
- ②. The soldering iron should not directly touch the capacitor.

8.3.3 无铅焊接曲线 Recommended Pb-Free soldering profile

回流焊 Reflow solder




电话(Tel): 86-768-6855949, 685923
 E-mail: market@china-threecircle.com

传真(Fax): (768) 6855928, 6855921
 Website: <http://www.cctc.cc/>

43

产 品 标 准 书	编 号
SPECIFICATIONFOR APPROVAL	Document No.
	DRAAW108H/0-2017

波峰焊接
Wave solder profile



8.4 分拨电路板 Handling

- Breakaway PC boards (splitting along perforations)
- (1).在电容器或其它贴装后，必须注意电路板弯曲或变形带来的应力。
 - (2).分拨电路板时必须使用专用的夹具，不可以用手拨断。
 - (1).When splitting the PC board after mounting capacitors and other components, care is required so as not to give any stresses of deflection or twisting to the board.
 - (2).Board separation should not be done manually, but by using the appropriate devices.

8.5 保存 Storage

- (1).在下列环境中保存产品：温度 5~40℃；湿度 ≤70% RH
- (2).产品自生产之日保存期为一年，产品使用之前请勿拆开编带。
- (3).编带拆开后，产品应在三个月内使用。
- (4).高介电常数电容器（X7R,X5R,Y5V）的容值随时间会逐渐减小，所以在电路设计时应充分考虑这一现象。容值减小的电容器在 150℃热处理 1 小时后容值会恢复到初始值。
- (1). Keep the storage environment conditions as following: Temperature: 5~40℃； Humidity: ≤70% RH
- (2). Don't open the tape until the parts are to be used, and store them within one year since the date printed on the reel.
- (3). Use the chips within 3 months after the tape is opened.
- (4). The capacitance value of high dielectric constant capacitors (X7R,X5R,Y5V) will gradually decrease with the passage of time, so this should be taken into consideration in the circuit design. If such a capacitance reduction occurs, a heat treatment of 150℃ for 1 hour will return the capacitance to its initial level.